



INSULATION
JUST GOT COOLER

ArmaGel[®] DT

Flexible aerogel insulation
blanket for cryogenic and
dual-temperature applications

- // ASTM C1728 Compliant
- // More choice: 5, 10, 15 and 20 mm thicknesses
- // Integrated zero-perm vapour barrier
- // Flexible at cryogenic temperatures

www.armacell.com/armagel



 **armacell**[®]
ArmaGel[®]

TECHNICAL DATA – ARMAGEL DT

Brief description	ArmaGel DT is a flexible aerogel insulation blanket suitable for cryogenic and dual-temperature insulation applications. ArmaGel DT is compliant with ASTM C1728 Type IV, Grade 1A.
Material type	Aerogel insulation blanket with integrated zero-perm vapour barrier
Colour	Grey
Special features	ArmaGel DT is intended for use in cryogenic and cyclic operating conditions. The product is suitable for use in multi-layer applications with other insulation products including ArmaSound® Industrial Systems.
Product range	Sheets in rolls, 5, 10, 15 and 20 mm [0.2, 0.4, 0.6, 0.8] thickness and width of 1.5 m [59 in]. For further details, please refer to the product range tables at the end of this document.
Applications	Thermal insulation/protection of pipes, vessels and ducts (including elbows, fittings, flanges etc.) in cryogenic, offshore, industrial (typically oil and gas) and process equipment facilities. ArmaGel DT is also used as a component of ArmaSound Industrial Systems to provide acoustic insulation on industrial pipework and vessels, ensuring reduction of sound transmission.
Installation	For industrial applications, it is recommended to consult the relevant Armacell application manual(s). Please consult our Technical Services for further information and support.

Property	Value/Assessment	Standard/Test method
Temperature range¹		
Service temperature	Max. service temperature	+250 °C +482 °F
	Min. service temperature ¹	-180/-196 °C -292/-321 °F
Thermal conductivity		
Thermal conductivity ² (metric units)	θm	-129 -73.3 -17.8 +23.9 +37.8 +93.3 +149 +204 [°C]
	λd ≤	0.015 0.017 0.020 0.021 0.022 0.023 0.025 0.029 [W/(m·K)]
Thermal conductivity ² (imperial units)	θm	-200 -100 0 +75 +100 +200 +300 +400 [°F]
	λd ≤	0.10 0.12 0.14 0.14 0.15 0.16 0.17 0.20 [Btu·in/(h·ft ² ·°F)]
Temperature resistance		
Linear shrinkage under soaking heat	< 2% in width and length	Tested according to ASTM C356
Water absorption	Maximum 8%	Tested according to ASTM C1763
Fire performance & approvals		
Surface burning characteristics	≤ 25 flame spread index ≤ 50 smoke development	Tested according to ASTM E84
International Maritime Organisation (IMO)	Compliant to IMO Part 2 (smoke generation and toxicity) Compliant to IMO Part 5 (surface flammability)	Tested according to IMO 2010 FTP Code
Marine approval	Compliant with Module B of Directive 2014/90/EU. Certified by Bureau Veritas.	Tested according to MED 2014/90/EU Module B
Density		
Nominal density	185 kg/m ³ 11.5 lb/ft ³	Tested according to ASTM C303
Mechanical properties		
Compressive strength ³	≥ 5 psi/ 34.5 kPa at 10% compression	Tested according to ASTM C165
Classifying the flexibility of mineral fibre blankets	Flexible	Tested according to ASTM C1101
Corrosion mitigation		
Stress corrosion cracking	Insulation for use over austenitic steel: no cracks, passed	Tested according to ASTM C692, ASTM C795
Corrosiveness of steel	Passed, Mass Loss Corrosion Rate (MLCR) not exceeding that of 5 ppm chloride solution on carbon steel coupon	Tested according to ASTM C1617, procedure A
Water vapour transmission of integrated vapour barrier	0.00 perm	Tested according to ASTM E96



Other technical features

Weather resistance	In all industrial applications the outer layer of the material must be protected with an adequate covering like metal jacketing or preformed UV-cured GRP (Glass-Reinforced Plastic) cladding. Please contact Technical Services for guidance on the temperature limitations and specific construction considerations which need to be made for each jacketing system.	
Health aspects	Neutral	
Hydrophobic	Yes	
Water vapour sorption	≤ 5% by weight	Tested according to ASTM C1104
Fungal resistance	No growth	Tested according to ASTM C1338
Storage	Material shall be stored indoors, in clean and dry conditions, away from direct sunlight.	
Shelf (storage) life ⁴	Max. 3 years	

- ArmaGel DT is compliant with ASTM C1728 Type IV, Grade 1A with minimum use temperature of -196 °C. For operating temperatures below -180 °C, special attention must be given to the system design and craftsmanship during installation to ensure that the material does not come in contact with liquid oxygen. For further information and support, please contact Technical Services.
- Thermal conductivity measured under a load of 1.5 kPa (0.22 psi).
- Test performed with a preload of 13.8 kPa (2 psi).
- Shelf life (maximum storage time) is limited in order to make sure that only currently manufactured products are applied on projects. This limitation is restricted solely to storage of the product and does not affect the lifetime of product after it has been installed.

Sheets

		Metric sizes				Imperial sizes			
		Nominal thickness	Width	Length	Content per roll	Nominal thickness	Width	Length	Content per roll
		[mm]	[m]	[m]	[sqm]	[in]	[in]	[ft]	[sq ft]
Standard Rolls	AGD-05-00/150S	5	1.5	13	19.5	0.2	59	42.7	209.9
	AGD-10-00/150S	10	1.5	8	12	0.4	59	26.2	129.2
	AGD-15-00/150S	15	1.5	5.2	7.8	0.6	59	17.1	84.0
	AGD-20-00/150S	20	1.5	4	6	0.8	59	13.1	64.6
Jumbo Rolls	AGD-05-00/150P	5	1.5	80	120	0.2	59	262.5	1291.7
	AGD-10-00/150P	10	1.5	40	60	0.4	59	131.2	645.8
	AGD-15-00/150P	15	1.5	26	39	0.6	59	85.3	419.8
	AGD-20-00/150P	20	1.5	20	30	0.8	59	65.6	322.9
Tolerances	Thickness tolerances	5 mm (0.2 in) nominal thickness 10 mm (0.4 in) nominal thickness 15 mm (0.6 in) nominal thickness 20 mm (0.8 in) nominal thickness				± 1 mm ± 2.5 mm ± 3 mm ± 4 mm			
	Width tolerances					± 3%			
	Length tolerances					± 5%			

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our Data Protection Policy.

© Armacell, 2024. ArmaGel® is a trademark of the Armacell Group and is registered in the European Union and other countries.
00185 | ArmaGel DT | ArmaGel | TDS | 012024 | Global | EN MASTER

ABOUT ARMACELL

As the inventor of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With more than 3,300 employees and 27 production plants in 19 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams, and generated net sales of EUR 806 million and an adjusted EBITDA of EUR 121 million in 2022. Armacell focuses on insulation materials for technical equipment, high-performance foams for acoustic and lightweight applications, recycled PET products, next-generation aerogel technology and passive fire protection systems.

For more information, please visit:
www.armacell.com/armagel

