



INSULATION  
JUST GOT COOLER

# ArmaGel™ DT

Flexible aerogel insulation  
blanket for cryogenic and  
dual-temperature applications

- // Operating temperatures from -180 °C (-292 °F)  
to +250 °C (+482 °F)
- // More choice: 5, 10, 15 and 20 mm thicknesses
- // Integrated zero-perm vapour barrier
- // Flexible at cryogenic temperatures

[www.armacell.com/armagel](http://www.armacell.com/armagel)



 **armacell**<sup>®</sup>  
ArmaGel™

## TECHNICAL DATA – ARMAGEL DT

Brief description	ArmaGel DT is a flexible aerogel insulation blanket suitable for applications with operating temperatures between -180 °C [-292 °F] and +250 °C [+482 °F]
Material type	Aerogel insulation blanket with integrated zero-perm vapour barrier
Colour	Grey
Special features	ArmaGel DT is intended for use in dual temperatures and cyclic operating conditions between -180 °C [-292 °F] and +250 °C [+482 °F]. The product is suitable for use in multi-layer applications with other insulation products including ArmaSound® Industrial Systems.
Product range	Sheets in rolls, 5, 10, 15 and 20 mm [0.20, 0.39, 0.59, 0.79 in] thickness and width of 1.5 m [59.00 in]. For further details, please refer to the product range tables at the end of this document. Also available in 0.75 m width [29.53 in] upon request.
Applications	Thermal insulation/protection of pipes, vessels and ducts (including elbows, fittings, flanges etc.) in cryogenic, offshore, industrial (typically oil and gas) and process equipment facilities. ArmaGel DT is also used as a component of ArmaSound Industrial Systems to provide acoustic insulation on industrial pipework and vessels, ensuring reduction of sound transmission.
Installation	For industrial applications, it is recommended to consult the relevant Armacell application manual(s). Please consult our Technical Services for further information and support.

Property	Value/Assessment							Standard/Test method	
<b>Temperature range<sup>1</sup></b>									
Service temperature	Max. service temperature	+250 °C		+482 °F			Tested according to ASTM C411		
	Min. service temperature	-180 °C		-292 °F					
<b>Thermal conductivity</b>									
Thermal conductivity <sup>1</sup> (metric units)	θm	-129	-73.3	-17.8	+23.9	+37.8	+93.3	[°C]	Tested according to ASTM C177
	λd ≤	0.015	0.018	0.020	0.021	0.022	0.023	[W/(m·K)]	
Thermal conductivity <sup>1</sup> (imperial units)	θm	-200	-100	0	+75	+100	+200	[°F]	
	λd ≤	0.10	0.12	0.14	0.15	0.15	0.16	[Btu·in/(h·ft <sup>2</sup> ·°F)]	
<b>Temperature resistance</b>									
Linear shrinkage under soaking heat	< 2% in width and length							Tested according to ASTM C356	
Water absorption	Maximum 8%							Tested according to ASTM C1763	
<b>Fire performance &amp; approvals</b>									
Surface burning characteristics	< 25 flame spread index < 50 smoke development							Tested according to ASTM E84	
International Maritime Organisation (IMO)	Compliant to IMO Part 2 (smoke generation and toxicity) Compliant to IMO Part 5 (surface flammability)							Tested according to IMO 2010 FTP Code	
<b>Density</b>									
Density	160 to 240 kg/m <sup>3</sup>		10 to 15 lb/ft <sup>3</sup>				Tested according to ASTM C303		
<b>Mechanical properties</b>									
Compressive strength <sup>2</sup>	>5 psi/ 34.5 kPa		at 10% compression				Tested according to ASTM C165		
Classifying the flexibility of mineral fibre blankets	Flexible							Tested according to ASTM C1101	
<b>Corrosion mitigation</b>									
Stress corrosion cracking	Insulation for use over austenitic steel: no cracks, passed							Tested according to ASTM C692, ASTM C795	
Corrosiveness of steel	Passed, Mass Loss Corrosion Rate (MLCR) not exceeding that of 5 ppm chloride solution on carbon steel coupon							Tested according to ASTM C1617, procedure A	
Water vapour transmission rate of integrated vapour barrier	0.00 perm							Tested according to ASTM E96	



### Other technical features

Weather resistance	In all industrial applications the outer layer of the material must be protected with an adequate covering like metal jacketing or preformed UV-cured GRP (Glass-Reinforced Plastic) cladding. Please contact Technical Services for guidance on the temperature limitations and specific construction considerations which need to be made for each jacketing system.		
Health aspects	Neutral		
Hydrophobic	Yes		
Water vapour sorption	≤ 5% by weight		Tested according to ASTM C1104
Fungal resistance	No growth		Tested according to ASTM C1338
Storage	Material shall be stored indoors, in clean and dry conditions, away from direct sunlight.		
Shelf (storage) life <sup>*3</sup>	Max. 3 years		

1. For temperatures below or above those published please contact Technical Services to request the corresponding technical information.
2. Test performed with a preload of 2 psi.
3. Shelf life (maximum storage time) is limited in order to make sure that only currently manufactured products are applied on projects. This limitation is restricted solely to storage of the product and does not affect the lifetime of product after it has been installed.

### Sheets

		Metric sizes				Imperial sizes			
		Nominal thickness	Width	Length	Content per roll	Nominal thickness	Width	Length	Content per roll
		[mm]	[m]	[m]	[sqm]	[in]	[in]	[ft]	[sq ft]
<b>Standard Rolls</b>	<b>AGD-05-00/150S</b>	5	1.50	13.00	19.50	0.20	59.00	42.65	209.90
	<b>AGD-10-00/150S</b>	10	1.50	8.00	12.00	0.39	59.00	26.25	129.17
	<b>AGD-15-00/150S</b>	15	1.50	5.20	7.80	0.59	59.00	17.06	83.96
	<b>AGD-20-00/150S</b>	20	1.50	4.00	6.00	0.79	59.00	13.13	64.59
<b>Jumbo Rolls</b>	<b>AGD-05-00/150P</b>	5	1.50	65.00	97.50	0.20	59.00	213.26	1049.48
	<b>AGD-10-00/150P</b>	10	1.50	40.00	60.00	0.39	59.00	131.24	645.84
	<b>AGD-15-00/150P</b>	15	1.50	26.00	39.00	0.59	59.00	85.31	419.80
	<b>AGD-20-00/150P</b>	20	1.50	20.00	30.00	0.79	59.00	65.62	322.92
<b>Tolerances</b> According to ASTM C1728	<b>Thickness tolerances</b>	5 mm (0.20 in) nominal thickness 10 mm (0.39 in) nominal thickness 15 mm (0.59 in) nominal thickness 20 mm (0.79 in) nominal thickness				5.0 - 7.0 mm 10.0 - 12.5 mm 15.0 - 17.5 mm 20.0 - 22.5 mm			
	<b>Width tolerances</b>	± 3%							
	<b>Length tolerances</b>	± 5%							

\* Rolls of 0.75 m (29.53 in) width are available upon request.

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer or contract. By ordering/receiving product you accept the **Armacell General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these.

© Armacell, 2020. All trademarks followed by ® or TM are trademarks of the Armacell Group.  
00185 | ArmaGel DT | ArmaGel | TDS | 032020 | Global | EN MASTER

## ABOUT ARMACELL

---

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,100 employees and 24 production plants in 16 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

For more information, please visit:  
[www.armacell.com/armagel](http://www.armacell.com/armagel)

