



TECHNICAL DATA

ArmaPET[®] Struct FR

ArmaPET Struct is the versatile and durable solution for structural sandwich applications, with a more environmentally responsible approach.

- // Halogen-free product allows for low smoke and toxicity and enhances public safety
- // Exceeds the requirements of a large variety of international fire safety standards
- // Superior impact resistance ensures long-term performance, fewer repairs and easy maintenance
- // Sustainable PET solution, based on 100% recyclable material, allows for an eco-friendly way of travelling

www.armacell-core-foams.com




ArmaPET[®]

FIRE-RETARDANT STRUCTURAL FOAM CORE

ARMAPET STRUCT FR

With this **fire-retardant, self-extinguishing** version of ArmaPET Struct, we offer a structural foam core designed for applications with particularly stringent fire protection requirements.

SAFETY FIRST

ArmaPET Struct FR fire-retardant versions have been designed for but are not limited to the transportation and construction sectors and are certified according to the relevant fire safety standards, including NF F16-101, DIN 5510-2, EN 13823 and EN 45545-2.

// EN 45545-2

As a standalone foam, ArmaPET Struct FR complies with hazard level **HL2**, which covers 85 to 90% of all rail applications.

However, EN45545-2 does not require testing of the individual components, but in the final sandwich set-up. ArmaPET Struct FR in combination with phenolic or aluminium skins, for example, can be certified for levels up to **HL3**.

// EN 13823

SBI product classification can be influenced by the combination of density and thickness. ArmaPET Struct FR70 with a thickness of 25 mm achieves fire **class D**, whereas the same material with a thickness of 10 mm, achieves **class B**.

// Calorific value

Calorific value means the amount of heat released during complete combustion. The more heat is contributed to the fire, the faster the fire spreads. Consequently, the lower the material's calorific value, the better. Even though ArmaPET is not incombustible, its calorific value is lower than that of other materials currently on the market, which

means it contributes less to the spread of a fire. For ArmaPET Struct FR150, for example, the value is **23 MJ/kg**.

// Halogen-free

For this fire-retardant version of ArmaPET Struct, we only use **halogen-free, flame-retardant additives**.

In a fire, ArmaPET Struct FR, with its very low smoke generation and reduced smoke toxicity, improves fire safety in terms of escape time and potential health damage.

APPLICATIONS

In addition to its excellent fire safety performance, ArmaPET Struct FR provides a durable final product solution with high impact resistance for long-term performance, fewer repairs and easy maintenance.

TRANSPORTATION: body structure / floor / door / interior of tram, train, bus or coach

CONSTRUCTION: building envelope / domes / modular housing



Technical Data

ArmaPET Struct FR

			FR70	FR100	FR150
Density	ISO 845	kg/m ³	70 ⁽¹⁾	100 ⁽¹⁾	150 ⁽²⁾
		lb/ft ³	4.4 ⁽¹⁾	6.2 ⁽¹⁾	9.4 ⁽²⁾
Compression Strength	ISO 844	MPa	0.8	1.5	2.3
		psi	115	220	335
Compression Modulus	ISO 844	MPa	40	70	105
		psi	5'800	10'150	15'225
Shear Strength ⁽³⁾	ISO 1922	MPa	0.55	0.8	1.3
		psi	80	115	190
Shear Modulus ⁽³⁾	ISO 1922	MPa	14	20	40
		psi	2'030	2'900	5'800
Shear Strain ⁽³⁾	ISO 1922	%	20	15	8
		%	20	15	8
Tensile Strength	ASTM C 297	MPa	1.6	2.4	2.9
		psi	230	350	420
Tensile Modulus	ASTM C 297	MPa	60	105	160
		psi	8'700	15'225	23'200
Thermal Conductivity *	at 23 °C	W/(m·K)	0.034	0.034	0.041
		at 73.4 °F	BTU.in/ FT ² .hr.°F	0.236	0.236

Fire Performance ⁽⁴⁾

Flammability *	DIN 5510-2	S4	S4	S4
Smoke Density *	DIN 5510-2	SR2	SR2	SR2
Dripping *	DIN 5510-2	ST2	ST2	ST2
Toxicity (FED) *	DIN 5510-2	<0.1	<0.1	<0.1
Edge Ignition *	DIN 5510-2	K1	K1	K1
Flammability	NF F16-101	M1 ⁽⁵⁾	M1 ⁽⁶⁾	M1 ⁽⁶⁾
Smoke Density *	NF F16-101	F1	F1	F1
FST *	EN 45545-2 ⁽⁷⁾	conform	conform	conform
Contribution to fire	EN 13823	B ⁽⁸⁾	C ⁽⁸⁾	C ⁽⁸⁾
Smoke Production	EN 13823	s1 ⁽⁸⁾	s1 ⁽⁸⁾	s2 ⁽⁸⁾
Flaming Droplets	EN 13823	d0 ⁽⁸⁾	d0 ⁽⁸⁾	d0 ⁽⁸⁾

Tolerances

		Length	Width	Diagonal	Thickness
Dimensions ⁽⁹⁾	mm	2448	1008	⁽¹⁰⁾	5-150 mm
	inch	96.38	39.68	⁽¹⁰⁾	0.2 - 5.9
At room temperature	mm	+/- 5	+/- 5	≤ 4	≤ 100mm: +/- 0.5 ≥ 100mm: +/- 1
	inch	+/- 0.2	+/- 0.2	≤ 0.16	≤ 3.94: +/- 0.02 ≥ 3.94: +/- 0.04

(*) Based on single test results, to be used for information only.

(1) Tolerances: +/- 5 kg/m³, +/- 0.3 lb/ft³

(2) Tolerances: +/- 5 %

(3) // direction (parallel to the weld)

(4) For detailed test results and certificates please contact us.

(5) 10 to 25 mm, 0.39 to 0.79 inch.

(6) As of 15 mm, 0.59 inch.

(7) Final sandwich design to be tested.

(8) At 10 mm.

(9) Standard dimension. Further dimensions on special request.

(10) Depending on length and width combination.

All values are average production figures. Minimum values on request.

Our products are CFC / HFC free.

Only halogen-free flame retarded additives.

Physical properties are not affected by variances in colour.

Customs tariff code: 39.21.19.00

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our [Data Protection Policy](#).

© Armacell, 2021. All rights reserved. ™ is a trademark of the Armacell Group.
00482 | Arma PET Struct FR | ArmaPET | C_TDS | 102021 | Global | EN Master

ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,000 employees and 23 production plants in 15 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

For more company information, please visit:
www.armacell.com

For product information, please visit:
www.armacell-core-foams.com

